

# **Chelfix Proof 205 Flex**

Cement and Acrylic Based, Two Component, Full Elastic Waterproofing Material



### In accordance with, EN14891, EN1504-2

Deal of Deal dates	It is a two component, full elastic waterproofing material consisting of a combination of		
Product Description	liquid polymers and special additives.		
Areas of Usage	<ul> <li>In concrete and cement mortars and plastered surfaces in indoor and outdoor environments, as waterproofing,</li> <li>For curtain and wall insulation,</li> <li>Concrete is made in non-moving areas,</li> <li>For wet volume waterproofing,</li> <li>Water storage, swimming and ornamental pools,</li> <li>Wet spaces such as bathroom, wc, balcony,</li> <li>It is used in engineering constructions such as metro, tunnel, dam, highway.</li> </ul>		
Features and Benefits	<ul> <li>Can be used indoors and outdoors. When applied in outdoors, it is necessary to cover the floor.</li> <li>Drinking water is suitable for the theme.</li> <li>It does not shrink or crack.</li> <li>It is suitable for horizontal and vertical applications.</li> <li>It does not contain corrosive and toxic substances and can be used in drinking water tanks.</li> </ul>		
Application Instructions	The surfaces must be clean, smooth, solid, free from any antiadhesive substance such as dust, oil, dirt, rust, mold oil, detergent and waste. If there is segregation in concrete, broken and loose parts should be removed. If there is crack, hollow on the floor or wall to be applied, it should be repaired with appropriate repair mortars. CHELFIX PROOF 205 Flex should be applied 3-4 days later. Make sure that the slab or concrete is thrown in the direction of the water stream. The correct control of the curve is made in the following way. Beginning from the beginning to the gauge, put a scale on it. If it is determined that there is no inclination or reverse slope in the control result, the application should not be started and the direction of the water flow should be adjusted by performing concrete and slab treatment. If necessary, additional screed or concrete must be poured. If the surface to be insulated is dry, it should be made ready for application by ensuring that it becomes wet and saturated with water. Tapered corners and edges should be chamfered with thick repair mortar. Champer Tapes should be applied to all the corners before ceramic tiles on wet floors and balconies. After CHELFIX PROOF 205 Flex is thoroughly mixed and rested, the water is applied to the saturated surface with the help of a brush and trowel without losing its moisture. Following the first coat, second coat is applied in the perpendicular direction of the first coat. If application is made on screed, flexible waterproofing files should be used between floors. Waiting time between floors; After the application of CHELFIX PROOF 205 Flex is first poured into a clean container which is free from all sorts of substances that prevent adhesion. The compound CHELFIX PROOF 205 Flex A in powder form is then poured slowly. The product is mixed with a low speed mixer until a homogeneous mixture without lumps is obtained. Mixing time should be at least 5 minutes, the mortar obtained at the end of the process should be rested for 3 minutes and mi		



#### Application Notes / Restrictions

- Since it's cement based, do not breathe it dust, prevent contact it with skin and hands.
- Do not apply to wood, chipboard, mdf, plywood, PVC and metal surfaces.
- Only the liquid should be used in the mixture. Absolutely no water should be added.
  - Foreign materials should not be added.
  - Thick application should be avoided in one go.
  - Protection is required to achieve long-term performance expected from the product. Tiles, ceramics, plaster and screed should be applied after 3 days in order to protect against punctures, scratches and crushes which may occur after application.
  - it must be protected after application against adverse weather conditions such as direct sunlight, high air temperature (above +35°C), rain and frost. The product should be cleaned thoroughly with water and detergent before it is fully cured and hardened.
- Immediately after application, before hardened, the equipment should be cleaned with water. After the product is hardened, it should be cleaned by mechanical methods.

## **Technical Data**

General Information				
Color	A Component grey, powder; B Component white, liquid			
The Color of the Mixture	Grey			
Package	30 kg set			
Shelf Life	12 months in unopened package in dry environment			
Application Information				
Mixture Density	1,8 (± 0,04) kg / lt			
Time to Put into Service	At least 3 days			
Performance Information				
Adhesion Strength	≥ 1 (28 days) N/mm <sup>2</sup> (TS EN 1542)			
Water Transfer Rate	< 0.1 kg / m²/h) (TS EN 1062-3)			
Water Vapor Transfer Rate	< 0.6 gr / (h.cm <sup>2</sup> ) (TS EN ISO 7783-2)			
Pressurized Water Resistance	5 Bars Positive			
Heat Resistance of the Cured Product	(-25°C) - (+80°C)			
Hazardous Substances	According to Article 5.3			
Fire Response	Bs1d0			
Quality Certificate	TS EN 1504-2, EN 14891			

# **Consumption Table**

Chelfix Proof Flex 205	Mixture Density (kg / liter)	1m <sup>2</sup> for 2 floors Powder Consumption (kg)
30 kg set	~1,8 (± 0,04) kg / lt	2,5 - 3,0